

65-45-12 Ductile Iron

Description

Dura-Bar 65-45-12 ductile iron contains nodular graphite in a matrix of ferrite with small amounts of pearlite. The ferritic structure gives excellent machinability with good surface finishes along with optimal impact strengths, fatigue properties, electrical conductivity and high magnetic permeability. This iron has approximately the same tensile and yield strengths as AISI 1018 steel in the as-rolled condition. This specification conforms to ASTM A536 grade 65-45-12

Applications

Oil/Gas:

Pony Rods, Plungers, Crossheads, Seals, Valves and valve seats

Fluid Power:

Cylinder Blocks, End Caps, Gear Rack Housings, Gerotors, Glands, Manifolds, Pistons, Rotors, Valves

Automotive:

Gears

Glass Mold:

Bank Molds, Plungers

Machinery:

Bushings, Chuck Bodies, Die Blocks, Flywheels, Gears, Housings, Journals, Pulleys, Rams, Rotary Tables, Side Frames, Spindle Housings, Tie Rod Nuts

Miscellaneous:

Plunger Pin

Power Transmission:

Coupling Hubs, Gears, Pulleys, Sprockets

Pump/Compressor:

Gears, Housings, Pistons, Rotary Screws, Rotors

Transportation:

Coupling Hubs, Gears, Pulleys, Rail Spacers, Sprockets

Physical Properties

Property	Measurement
Density (lbs/in ³)	0.255
Poisson's ratio [ν]	Min: .2875 ; Max: .2925
Modulus of elasticity (Tension) (psi) [E]	23-25E ⁶
Modulus of rigidity (Shearing) (psi) [G]	9,803,922
Thermal conductivity (BTU/Hr/ft ² /inch/°F), (Range: Room Temp - 212°F)	18.68
Thermal expansion coefficient(/°F) [α], (Range: 70 - 212°F)	6.40E-06
Damping capacity	5 - 20*
Electrical Resistivity (Microhms x Cm)	75-80 **
Magnetic properties (KiloGauss/Oersteds@100 Oersteds)	High permeability, low coercive force
Heat treat response (Rc)	55-60

* Damping = ability of material to quell vibration through elastic hysteresis. Expressed as percentage of total energy/ amplitude lost in one complete stress-strain cycle. Damping can be related to chemical analysis/composition and microstructure.

** Specific resistivity of all irons increases with temperature. Chemical composition and microstructure also play roles in determining electrical resistivity. Increasing amounts of carbon/silicon increase ER.

Mechanical Properties

Hardness properties for various diameters are shown in the table. Hardness properties listed are minimum and maximum across the bar. For rectangles, squares and shapes, the hardness properties will depend on minimum and maximum section thickness and will be supplied on request.

Size Range		BHN	
Inches	mm	Min	Max
01.000 - 02.000	25 - 51	156	217
02.001 - 03.000	51 - 76	153	207
03.001 - 06.000	76 - 152	143	207
6.001 - 20.000	152 - 508	131	207

Tensile strength is determined from a longitudinal test specimen taken from mid-radius of the as-cast bar. In bars under 2.0 " diameter, elongation will be 9% minimum.

Mechanical Properties	
Tensile strength psi (min)	65,000
Yield strength psi (min)	45,000
Elongation (min)	12%

Microstructure



The microstructure consists of Types I & II nodular graphite as defined in ASTM A247. The matrix is ferrite with approximately 5-25% pearlite. The edge or rim will have a higher nodular count and will be mostly ferrite. Chill carbides will be less than 5% in any field at 100x and will be well dispersed.

Machinability



* Based on 1212 steel = 100%

Heat Treat Response

Dura-Bar 65-45-12 can be oil quench hardened from 1600° F (885° C) to Rockwell C 50 minimum on the outside of the bar. Hardness in the core will be less than the hardness on the outside surfaces. Any grade of ductile iron can be quenched and tempered to 50 – 55 Rc. This grade also responds well to surface hardening methods such as flame or induction heat treating. It is well suited for austempering because of the low residual alloy content, and the highly ferritic matrix provides predictable growth with minimal heat-distortion. Get more details including typical Jominy end quench curve, methods and cycle times, and temperature effects by downloading the Dura-Bar Heat Treating Guide.

Chemical Composition

Element	Percentage
Carbon*	3.50 - 3.90%
Silicon*	2.25 - 3.00%
Manganese	0.15 - 0.35%
Sulfur	0.025% Max
Phosphorus	0.05% Max

*Carbon and silicon targets are specified for each bar size in order to maintain mechanical properties. Magnesium is added as an inoculant to produce nodular graphite.

Applicable Specifications

ASTM A536

Forms Manufactured

Rounds: 1.250" to 8.250"

Rectangles: 2.030" x 2.530" to 20.000" x 25.600"

Squares: 2.030" x 2.030" to 21.000" x 21.000"

Custom shapes available per request

Disclaimer

All of the above information is for reference only. Actual results are influenced by process variables and actual size of the raw material.

Visit www.dura-bar.com/applications/index.cfm to see successful applications being made from Dura-Bar, including their design and cost benefits. Contact us today to discuss your application and how you can start saving with Dura-Bar.