



**Bronze Family:** High Tin Bronze

**Solids:** 1" to 6" OD

**Tubes:** 1" to 6" OD

**Rectangles:** Up to 10"

**Standard Lengths:** 144"

## CHEMICAL COMPOSITION

Alloy	Cu% <sup>1</sup>	Sn%	Pb%	Zn%	Fe%	Ni% <sup>2</sup>	Sb%	P% <sup>3</sup>	S%	Al%	Mn%	Si%
C90810	Rem	11.00- 13.00	0.25	0.30	0.15	0.50	0.20	0.15- 0.80	0.05	0.005	N/A	0.005

<sup>1</sup>In determining Cu min., Cu may be calculated as Cu + Ni.    <sup>2</sup>Ni Value includes Co.    <sup>3</sup>For continuous castings, P shall be 1.5% max

Note: Cu + Sum of Named Elements, 99.4% min.